



**SHERWIN
WILLIAMS®**

SWP® Exterior Oil Base Gloss

A02W00026 White
A02W00528 Tinting White
A02W00053 Deep Base
A02T00054 Ultradeep Base

As of 12/07/2016, Complies with:			
OTC	No	LEED® 09 NC, CI	N/A
OTC Phase II	No	LEED® 09 CS	N/A
SCAQMD	No	LEED® 09 H&S	N/A
CARB	No	LEED® v4 Emissions	N/A
CARB SCM 2007	No	LEED® v4 VOC	No
Canada	No	MPI	

CHARACTERISTICS

SWP Exterior Gloss Oil Base Paint is our best quality oil base house and trim product. This product is recommended for use on wood siding, clapboard, shakes, shingles, plywood, rough sawn lumber, masonry, and metal.

Color: Most colors
To optimize hide and color development, always use the recommended P-Shade primer

Coverage: 350 - 400 sq ft/gal
@ 4 mils wet; 2.1 mils dry

Drying Time, @ 77°F, 50% RH:

Touch: 4-6 hours
Recoat: 24 hours

Drying and recoat times are temperature, humidity and film thickness dependent.

Flash Point: 118°F, PMCC

Finish: Gloss 80 units @ 60°

Tinting with Blend-A-Color:

Base	oz/gal	Strength
Tinting White	0-5	Sher-Color
Deep Base	4-12	Sher-Color
Ultradeep Base	4-12	Sher-Color

Package White available

Vehicle Type: Alkyd

A02W00528

VOC (less exempt solvents):

371 g/L; 3.10 lb/gal

As per 40 CFR 59.406 and SOR/2009-264, s.12

Volume Solids: 52 ± 2%

Weight Solids: 66 ± 2%

Weight per Gallon: 9.23 lb

SPECIFICATIONS

Aluminum

1ct. Galvite HS
2cts. SWP Exterior Gloss Oil Base Paint

Galvanized Steel

1ct. Galvite HS
2cts. SWP Exterior Gloss Oil Base Paint

Masonry/Stucco

1ct. Loxon Concrete & Masonry Primer
2cts. SWP Exterior Gloss Oil Base Paint

Plywood

1ct. Exterior Latex Wood Primer
2cts. SWP Exterior Gloss Oil Base Paint

Steel, alkyd primer

1ct. All Surface Enamel Primer
2cts. SWP Exterior Gloss Oil Base Paint

Wood, Composition Board

1ct. Exterior Oil-Based Wood Primer
2cts. SWP Exterior Gloss Oil Base Paint

Other primers may be appropriate.

When repainting involves a drastic color change, a coat of primer will improve the hiding performance of the topcoat color.

SURFACE PREPARATION

WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (**NIOSH** approved) and proper containment and cleanup. For more information, call the National Lead Information Center at **1-800-424-LEAD** (in US) or contact your local health authority.

Remove all surface contamination by washing with an appropriate cleaner, rinse thoroughly and allow to dry. Scrape and sand peeled or checked paint to a sound surface. Sand glossy surfaces dull. Seal stains from water, smoke, ink, pencil, grease, etc. with the appropriate primer/sealer. Recognize that any surface preparation short of total removal of the old coating may compromise the service length of the system.

Aluminum and Galvanized Steel

Wash to remove any oil, grease, or other surface contamination. All corrosion must be removed with sandpaper, wire brush, or other abrading method.

Caulking

Fill gaps between windows, doors, trim, and other through-wall openings with the appropriate caulk after priming the surface.

Cement Composition Siding/Panels

Remove all dirt, dust, grease, oil, loose particles, laitance, foreign material, and peeling or defective coatings. Allow the surface to dry thoroughly. If the surface is new, test it for pH, if the pH is higher than 9, prime with Loxon Concrete & Masonry Primer.



SWP[®]

Exterior Oil Base Gloss

- A02W00026 White
- A02W00528 Tinting White
- A02W00053 Deep Base
- A02T00054 Ultradeep Base

<u>SURFACE PREPARATION</u>	<u>APPLICATION</u>	<u>CAUTIONS</u>
<p>Masonry, Concrete, Cement, Block All new surfaces must be cured according to the supplier's recommendations—usually about 30 days. Remove all form release and curing agents. Rough surfaces can be filled to provide a smooth surface. If painting cannot wait 30 days, allow the surface to cure 7 days and prime the surface with Loxon Concrete & Masonry Primer. Cracks, voids, and other holes should be repaired with an elastomeric patch or sealant.</p> <p>Mildew Prior to attempting to remove mildew, it is always recommended to test any cleaner on a small, inconspicuous area prior to use. Bleach and bleaching type cleaners may damage or discolor existing paint films. Bleach alternative cleaning solutions may be advised. Mildew may be removed before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach/water solution.</p> <p>Steel Remove all corrosion by abrading the surface. Bare steel must be primed the same day as cleaned.</p> <p>Wood, Plywood, Composition Board Clean the surface thoroughly then sand any exposed wood to a fresh surface. Patch all holes and imperfections with a wood filler or putty and sand smooth. Prime with appropriate primer. Knots and some woods, such as redwood and cedar, contain a high amount of tannin, a colored wood extract. If applied to these bare woods, it may show some staining. If staining persists, spot prime severe areas with 1 coat of Exterior Oil-Based Wood Primer prior to using.</p>	<p>Apply at temperatures above 50°F. No reduction needed.</p> <p>Brush Use a natural bristle brush.</p> <p>Roller Use a 3/8" - 3/4" nap synthetic cover.</p> <p>Spray—Airless Pressure2000 psi Tip......015"-.021"</p> <p><u>CLEANUP INFORMATION</u> Clean spills, spatters, and tools immediately after use with compliant solvent. After cleaning, flush spray equipment with a compliant cleanup solvent to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using solvents.</p>	<p>For exterior use only</p> <p>Before using, carefully read CAUTIONS on label.</p> <p>DANGER: Rags, steel wool, other waste soaked with this product, and sanding residue may spontaneously catch fire if improperly discarded. Immediately place rags, steel wool, other waste soaked with this product, and sanding residue in a sealed, water-filled, metal container. Dispose of in accordance with local fire regulations.</p> <p>HOTW 12/07/2016 A02W00528 53 371</p> <p>The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative or visit www.paintdocs.com to obtain the most current version of the PDS and/or an SDS.</p>