



**SHERWIN
WILLIAMS.**

106.06

WOOD CLASSICS[®] FastDry Sanding Sealer

B26V43

As of 04/27/2017, Complies with:			
OTC	No	LEED [®] 09 NC, CI	No
OTC Phase II	No	LEED [®] 09 CS	No
SCAOMD	No	LEED [®] 09 H&S	No
CARB	No	LEED [®] V4 Emissions	No
CARB SCM2007	No	LEED [®] V4 VOC	No
Canada	No	MPI	Yes

CHARACTERISTICS

The **Wood Classics System** is designed for use on architectural wood in commercial, institutional, and residential new construction and also for refinishing.

Wood Classics FastDry Sanding Sealer provides a high build surface and sands fast, easy, and effectively in 1 hour, giving an extremely smooth surface for topcoating. The Sanding Sealer provides an alternative to the first coat of varnish in a 2 coat system.

Wood Classics FastDry Sanding Sealer can be topcoated in 1½ hours with most clear alkyd topcoats.

Color: Clear Amber
Coverage: 350 - 500 sq ft/gal
3.5 - 4.5 mils wet; 1.0 - 1.3 mils dry

Drying Time, @ 77°F, 50% RH:
To touch: 20 minutes
To sand: 1 hours
To topcoat: 1-1/2 hours
Drying and recoat times are temperature, humidity, and film thickness dependent

Finish: 45-65 units @ 60°
Flash Point: 50°F, TCC
Vehicle Type:
Linseed Vinyl Toluene Alkyd

B26V00043

VOC (less exempt solvents): 542 g/L; 4.52 lb/gal
As per 40 CFR 59.406 and SOR/2009-264, s.12
Volume Solids: 29 ± 2%
Weight Solids: 35 ± 2%
Weight per Gallon: 6.95 lb

SPECIFICATION

Suggested system:

Smoothness and Speed

- 1st: Wood Classics Stain (optional)
- 2nd: Wood Classics *FastDry* Sanding Sealer
- 3rd: Wood Classics *FastDry* Oil Varnish

Not for use on floors.

Do not use under Polyurethane Varnish or lacquers.

Shading with Wood Classics Stain:

Base	oz/gal	Strength
Clear	0-2	not controlled

Tinting with Blend-A-Color Toner:

Base	oz/gal	Strength
Clear	0-1	not controlled

White or light colors

When used over a white or very light stain color this product will impart a slight yellow cast to the final appearance.

SURFACE PREPARATION

WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (**NIOSH** approved) and proper containment and cleanup. For more information, call the National Lead Information Center at **1-800-424-LEAD** (in US) or contact your local health authority.

Wood must be dry and cleaned of dirt, grease, wax, polish, and marks. Old finishes in poor condition should be completely removed and the surface treated as a new surface. Recognize that any surface preparation short of total removal of the old coating may compromise the service length of the system.

New wood should be stored inside for a minimum of 24 hours prior to staining. Stain or varnish applied to wood that has not been dried thoroughly can exhibit blotching, discoloration, or cracking.

Sand wood to a smooth surface using 100-120 grit paper. Remove sanding dust with a vacuum or tack cloth.

Avoid sanding wood that has only stain on it, sanding will remove some of the stain creating an uneven appearance.



WOOD CLASSICS[®]

FastDry Sanding Sealer

B26V43

<u>APPLICATION</u>	<u>CLEANUP INFORMATION</u>	<u>CAUTIONS</u>
<p>Be sure the temperature is above 50°F, and the humidity is below 85%. Do not shake. Stir Satin gently during use.</p> <p>No reduction necessary.</p> <p>Brush—Use a natural bristle brush. Brush out evenly, avoid unnecessary brushing into already coated areas. Avoid over-brushing which causes bubbling.</p> <p>Spray—Airless Pressure2000 psi Tip..... .008" - .013"</p> <p>Spray—Conventional Air Pressure50 psi Fluid Pressure..... 10-20 psi Cap/Tip 704/FF</p> <p>HVLP Unit Graco 3800 or 4900 Gun 960 Tip..... 1.4 -1.6 mm</p> <p>Staining may raise the grain of the wood, developing a slight texture. After the first coat of sealer is applied, if sanding is needed to eliminate this texture, allow 1 hour drying before sanding. Very lightly scuff sand between coats using 180 or finer grit sandpaper.</p> <p>If no stain is used, allow to dry 1 hour then sand with 180 or finer grit sandpaper.</p> <p>Although not as effective as sandpaper, steel wool and synthetic abrasive pads may be used for very light sanding.</p> <p>Remove all sanding dust with a tack cloth or vacuum.</p>	<p>Clean spills, spatters and tools immediately after use with compliant cleanup solvent. Follow manufacturer's safety recommendations when using solvents.</p> <p>DANGER Rags, steel wool, other waste soaked with this product, and sanding residue may spontaneously catch fire if improperly discarded. Immediately place rags, steel wool, other waste soaked with this product, and sanding residue in a sealed, water-filled, metal container. Dispose of in accordance with local fire regulations.</p>	<p>Non-Photochemically Reactive For interior use only. Do not use on floors.</p> <p>Before using, carefully read CAUTIONS on label.</p> <p>HOTW 04/27/2017 B26V00043 11 542</p> <p>The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative or visit www.paintdocs.com to obtain the most current version of the PDS and/or an SDS.</p>