



**SHERWIN
WILLIAMS®**

113.50

SHER-CRETE®
Flexible Concrete
Waterproofers - Textured
A05W00005 Extra White
A5W00053 Deep Base

As of 05/16/2017, Complies with:			
OTC	Yes	LEED® 09 NC, CI	Yes
OTC Phase II	Yes	LEED® 09 CS	Yes
SCAQMD	Yes	LEED® 09 H	Yes
CARB	Yes	LEED® V4 Emissions	No
CARB SCM2007	Yes	LEED® V4 VOC	Yes
Canada	Yes	MPI	Yes

<u>CHARACTERISTICS</u>	<u>SPECIFICATIONS</u>	<u>SPECIFICATIONS</u>									
<p>Sher-Crete Flexible Concrete Waterproofers is an interior/exterior flexible and breathable waterproof coating based on a unique combination of acrylic resin and mineral aggregate.</p> <p>Use Sher-Crete Flexible Concrete Waterproofers to waterproof all types of above-or on-grade concrete and masonry including foundations, block walls, balconies, window and door openings, walkways, parapets, planter boxes, and vertical or horizontal concrete substrates.</p> <p>Advantages</p> <ul style="list-style-type: none"> Apply to fresh concrete (less than 28 days old) Can be applied over substrates with a high pH (up to 13) Primer not typically required over properly prepared surfaces Sher-Crete Flexible Concrete Waterproofers passes ADA requirements of slip resistance 	<p>Color: Most colors</p> <p>Coverage: 125 to 150 ft² per gal. 10 - 12 mils wet per coat</p> <p>2 coats of the Sher-Crete Flexible Concrete Waterproofers at 10 - 12 wet mils per coat and a surface with 10 or less pinholes per square foot is required for a waterproofing system. Coverage will vary depending on the porosity and texture of the substrate.</p> <p>For maximum protection and washability, 2 coats of the following clear coats are recommended:</p> <p>Interior and Exterior Use</p> <p>Low/Medium traffic pedestrian areas H&C Paver Sealer Gloss or Natural or H&C Concrete Sealer Wet Look</p>	<p>If a stucco finish is to be applied over the Sher-Crete Flexible Concrete Waterproofers, follow the stucco manufacturers recommendations.</p> <p>Drying Time, @ 77°F, 50% RH: temperature and humidity dependent</p> <p>Touch: 1 hour Recoat: 4 hours For foot traffic: 24 hours</p> <p>Finish: Flat Flash Point: N/A</p> <p>Tinting with CCE:</p> <table border="0"> <tr> <td>Base</td> <td>oz/gal</td> <td>Strength</td> </tr> <tr> <td>Extra White</td> <td>0-5</td> <td>SherColor</td> </tr> <tr> <td>Deep Base</td> <td>4-12</td> <td>SherColor</td> </tr> </table> <p>Vehicle Type: Acrylic</p> <p style="text-align: center;">Extra White A05W00005 (may vary by base)</p> <p>VOC (less exempt solvents): <50 g/L - 0.42 lb/gal As per 40 CFR 59.406 and SOR/2009-264, s.12</p> <p>Volume Solids: 52 ± 2% Weight Solids: 69 ± 2% Weight per Gallon: 12.72 lb</p>	Base	oz/gal	Strength	Extra White	0-5	SherColor	Deep Base	4-12	SherColor
Base	oz/gal	Strength									
Extra White	0-5	SherColor									
Deep Base	4-12	SherColor									

REPORT	TEST METHOD	TEST CRITERIA	TEST RESULTS
Tensile Strength	ASTM D-412	without mesh	100 psi
Elongation	ASTM D-412	without mesh	57%
Flexibility Mandrel Bend	ASTM D-522	28 days	Pass 1/8" @ 77° F Pass
Abrasion Resistance	ASTM D-4060 -90	1000 cycles – 24hr cure	0.01 gram loss
Water Absorption	ASTM D-570	24 hour immersion	17%
Water Vapor Permeability	ASTM D 1653		12 perms
Meets ADA Requirements for Coefficient of Friction		Static Coefficient of Friction	Kinetic Coefficient of Friction
	A05W00005	1.13	0.81
	A05W00053	1.09	0.81
Flame Spread Index:	ASTM E84	1/4" fiber cement board	10
Smoke Developed Index:	ASTM E84	1/4" fiber cement board	15

Typical values for material cured at 73° F (23° C) and 50% R.H. Product test results from A05W00005



SHER-CRETE®

Flexible Concrete Waterproofers - Textured

A05W00005 Extra White
A5W00053 Deep Base

SURFACE PREPARATION

WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at **1-800-424-LEAD** (in US) or contact your local health authority.

Remove all surface contamination by washing with an appropriate cleaner, rinse thoroughly and allow to dry. Existing peeled or checked paint should be removed. Recognize that any surface preparation short of total removal of the old coating may compromise the service length of the system.

Concrete, Stucco

Pressure clean to remove all dirt, dust, grease, oil, loose particles, laitance, foreign material, peeling and defective coatings, chalk, form release agents, moisture curing membranes, etc. Allow the surface to dry thoroughly.

Concrete and mortar must be cured at least 7 days at 75°F. On tilt-up and poured-in-place concrete, commercial detergents and sandblasting may be necessary to remove sealers, release compounds, and to provide an anchor pattern.

Use caution when preparing the substrate to create a uniform surface. Voids, cracks, crevices, and through-wall openings must be patched using Concrete & Masonry Sealant or Patch.

Stripe coat all inside and outside corners and edges with Sher-Crete Flexible Concrete Waterproofers.

APPLICATION

Vertical Wood Window & Door Jambs

Apply one coat of Sher-Crete Flexible Waterproofers at a rate of 70 – 90 square feet per gallon, achieving a total dry film thickness of 10 – 12 mils. Embed Sher-Crete 6" Blue Repair Mesh to reinforce the lower corners over the sill, across the sill, and up both sides of the lower corners approximately 4". Apply a second coat of the waterproofers over the mesh and around the window opening, in the return to the window flange.

Apply at temperatures between 50°F and 100°F.

Do not reduce.

Brush - Use a nylon/polyester brush.

Roller - Use a ¾" to 1½" nap synthetic roller cover.

Notched squeegee with backroll

Use proper finish roll application technique to avoid roller tracking.

Texture Sprayer-Low Pressure

Tip orifice..... 4

OVER-COATING

Sher-Crete Flexible Concrete Waterproofers can be used as a stand-alone product or may be over-coated to provide a surface that will be smoother and easier to keep clean and to improve the abrasion resistance in areas that see significant foot traffic.

Over-coating should be done after the Sher-Crete has dried for at least 4 hours (77°F and 50% RH) and before it is exposed to any use. Follow all application and dry time information found on the label and data page for the specific over-coat.

Slip Resistance

Some surfaces may require a slip resistant additive for safety. Add H&C SharkGrip® Slip Resistant Additive to the final coat applied following label directions. This product should not be used in place of a non-skid finish.

CLEAN UP

Clean spills, spatters, hands and tools immediately after use with soap and warm water. Cured material can only be removed mechanically. After cleaning, flush spray equipment with compliant cleanup solvent to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using solvents.

CAUTIONS

Protect from freezing.

Non-photochemically reactive.

Not recommended for roofing applications or as a primary waterproofing over occupied space.

Not recommended for bridging joints or dynamic cracks in concrete.

Not for use in areas subject to vehicle traffic.

Before using, carefully read **CAUTIONS** on label.

HOTW 05/16/2017 A05W00005 24 48

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative or visit www.paintdocs.com to obtain the most current version of the PDS and/or an SDS.