



SHER-WOOD® Hi-Bild Lacquer

Gloss..... T70CT1
 Medium Rubbed Effect T70FT1

<u>DESCRIPTION</u>	<u>CHARACTERISTICS</u>	<u>SPECIFICATIONS</u>
<p>SHER-WOOD® Hi-Bild Lacquers are HAPS Compliant, high quality, pale, nitrocellulose, clear lacquers for finishing interior wood products.</p> <p>Advantages:</p> <ul style="list-style-type: none"> • Meets the federal HAPS rule for wood finishes* • Fast drying • Excellent flow • Produces good build (without having exceptionally high weight or volume solids) • Excellent film clarity with pale color • Excellent adhesion, especially over Sher-Wood Vinyl Sealers such as T67F3, T67F5, T67F6 and T67F7 • Excellent cold check resistance • Excellent print resistance • Good color retention • Easy to rub • No reduction needed • Meets KCMA requirements over • Sher- Wood Vinyl Sealers T67F3 and T67F6 • Free of lead hazards as packaged in compliance with Consumer Product Safety Commission's (CPSC) 16 CFR Chapter II: Subchapter B, part 1303. <p>Air Quality Data: (Theoretical)</p> <ul style="list-style-type: none"> • Non-photochemically reactive • Volatile Organic Compounds (VOC) as packaged, maximum less exempt solvents 5.67 lb/gal, 680 g/L • Hazardous Air Pollutants (HAPS) as packaged, maximum less than 0.8 lbs/ lb of solids <p>An Environmental Data Sheet is available from your local Sherwin-Williams facility or at www.paintdocs.com</p> <p>*National Standards for Hazardous Air Pollutants (HAPS) Emissions for Wood Furniture Manufacturing Operations CFR40, Part 63, Subpart JJ</p>	<p>Color: Gardner 2 maximum</p> <p>Gloss: Gloss 85+ units MRE 30-34 units</p> <p>Weight Solids: 22 ± 2%</p> <p>Volume Solids: 15.3 ± 1%</p> <p>Viscosity: 27-32 seconds #2 Zahn Cup 21-25 seconds #4 Ford</p> <p><i>The above chart is for information only and should not be used as product specifications</i></p> <p>Recommended film thickness: Mils Wet 5.0-6.0 Mils Dry 0.7 - 0.9</p> <p>Spreading Rate (no application loss) @ 0.7-0.9 mil dft: 272-389 sq ft/gal</p> <p>Drying (77°F, 50% RH): To Touch: 10 minutes To Handle: 30 minutes To Recoat: 1 hour Force Dry: at 140°F 15 minutes to recoat 60 minutes to pack</p> <p>Flash Point: 23°F, Pensky-Martens Closed Cup</p> <p>Package Life: 2 years, unopened</p>	<p>Surface preparation</p> <p>Wood - New Work (interior only):</p> <p>Must be clean, dry, and finish sanded. Substrate should be free of grease, oil, dirt, fingerprints, and any contamination to ensure optimum adhesion and coating performance properties. Moisture content of wood should be 6 to 8%.</p> <p>Previously finished wood (interior only):</p> <p>Strip old finishes completely and remove all contaminants from the surface. Make sure surface is dry. Finish as new work</p> <p>Wood Finishing System:</p> <ol style="list-style-type: none"> 1. Sanding Sealer—Sher-Wood Hi-Bild Lacquer Sanding Sealer, T60FT2, or Sher-Wood Vinyl Sealers, T67F3, T67F5, T67F6 or T67F7. 2. Air dry 30 minutes, sand, and remove all sanding dust. 3. Topcoat with Sher-Wood Hi-Bild Lacquer . 4. For more depth and better appearance, apply a second coat <p>Testing: The information, data, and recommendations set forth in this Product Data Sheet are based upon test results believed to be reliable. However, due to the wide variety of substrates, substrate properties, surface preparation methods, equipment and tools, application methods, and environments, the customer should test the complete system for adhesion, compatibility and performance prior to full scale application.</p>

APPLICATION

Typical Setups

Can be sprayed warm, up to 115°F

Conventional Spray:

Air Pressure..... 50-65 psi
Fluid Pressure 6-7 psi
Reducer HAPS Compliant Lacquer
Thinner, R7K320
Reduction Rate..... as needed up to 5%

Airless Spray:

Pressure 1200 psi
Tip 010-.012"
Reduction Rate..... none

Air Assisted Airless:

Pressure 600-800 psi
Tip015"
Reduction Rate..... 10%
Reducer..... R6K18
R6K18 improves application

Cleanup:

Clean tools/equipment immediately after use with HAPS Compliant Lacquer Thinner, R7K320. Lacquer Thinner, R7K120 or R7K22 may also be used, but are not HAPS compliant.

Follow manufacturer's safety recommendations when using any solvent.

SPECIFICATIONS

Performance Tests:

Cold Check Resistance.....20 cycles
Print Resistance No print
2.7 mils dft, 12 hours air dry, at 77°F
in direct contact with 8 oz. duck cloth.

Household Chemicals Test

Panels were aged 21 days at room conditions, 5 drops of each item were placed under a watch glass for one hour. After removal, the finish was examined and the following results noted:

Vinegar.....no visual effect
Lemon Juice.....no visual effect
Oil Base Paintno visual effect
Latex Emulsion Paintno visual effect
VM&P Naphthano visual effect
Turpentineno visual effect
Orange Crayon.....no visual effect
Mayonnaise.....no visual effect
Sour Milkno visual effect
Margarineno visual effect
Butter.....no visual effect
Water.....no visual effect
Cooking fatno visual effect

Moisture Resistance:

Poor when used over T60FT2 or other lacquer sanding sealers. However, when used over a vinyl sealer such as T67F3 or T67F6, resistance is excellent. This allows for use on kitchen cabinets, since KCMA specifications will be met.

SPECIFICATIONS

Product Limitations:

- Customer urged to pretest system under shop conditions.
- Surface to be finished must be free from dirt or other foreign matter.
- Under humid conditions add 1-5% MAK R6K30 to prevent film blushing. Such drying conditions will lengthen time to harden.
- Agitate package contents, especially T70FT1, before using.
- Not recommended for exterior use
- Natural wood will change color by itself and clear wood finishes will not keep this from occurring.
- To maintain HAPS compliance, only reduce with HAPS compliant reducers.
- Total film thickness of systems must not exceed 4.0 mils DFT.

This finishing lacquer and all other nitrocellulose based lacquers will yellow over time. With wood tone stains, this yellowing actually makes a warmer, softer appearance. Where white stains, pickled finishes, or white basecoats are used, nitrocellulose lacquer should not be used because of the yellowing of the sealer and topcoat may be considered objectionable. In these situations, Sher-Wood Vinyl Sealer, T67F3, T67F5, T67F6 or T67F7 top-coated with Sher-Wood CAB-Acrylic Lacquer is recommended because of its non-yellowing characteristics. Sher-Wood Water White Conversion Varnish or Sher-Wood Acrylic Conversion Coating may also be used if a catalyzed system is desired.

All trademarks are the property of their respective owners.

CAUTIONS

FOR INDUSTRIAL SHOP APPLICATION ONLY

Thoroughly review product label and Material Safety Data Sheet (MSDS) for safety and cautions prior to using this product.

To obtain the most current version of the Environmental Data Sheet (EDS), Product Data Sheet (PDS), or Safety Data Sheet (SDS) please visit your local Sherwin-Williams facility or www.paintdocs.com.

Please direct any questions or comments to your local Sherwin-Williams facility.

Note: All purchases of products from Sherwin-Williams are exclusively subject To Sherwin- Williams' terms and conditions of sale which can be found [by following this link \(click here\)](#) Please review these terms and conditions Prior to the purchase of the products.

Sherwin-Williams warrants the product to be free of manufacturing defect in accordance with Sherwin-Williams' quality control procedures. Except for the preceding sentence, due to factors that are outside of Sherwin-Williams' control, including substrate selection, and customer handling, preparation, and application, Sherwin- Williams cannot make any other warranties related to the product or the performance of the product.

SHERWIN-WILLIAMS DISCLAIMS ALL WARRANTIES OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTY OF MERCHANTABILITY, THE IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE.

Liability for products proven to be defectively manufactured will be limited solely to replacement of the defective product or the refund of the purchase price paid for the defective product, as determined by Sherwin-Williams. Under no circumstances shall Sherwin-Williams be liable for indirect, special, incidental or consequential damages, lost profits or punitive damages arising from any cause whatsoever.