

Technical Data Sheet

- PU ANTIGRAFFITI GLOSSY

GENERAL FEATURES

This thermosetting powder contains Hydroxy-Polyester resins cured with fit curing agents, caprolactam free.

The powder forms a decorative film with enhanced outdoor resistance.

The product forms a level hard film with good resistance to mechanical damage, detergents, fuels and oils.

APPLICATION

Examples of their application are platform signage and train components, bus shelters, security lockers, telephone boxes, road and general signage, roller shutter doors, transformers, and furniture for industry and schools.

Potential applications include areas in public buildings and recreation grounds such as toilet and shower cubicles, wall partitioning, benches, outdoor furniture, fixing and fitting and in general in every application where is requested antigraffiti resistance, resistance to the spots, superficial hardness, arranged to the optimal aesthetic aspect.

Designs with varnishes in cylinders spray can be easily removed using xylene, acetone or trichloroethylene.

ADVISED CYCLES

The surface to be coated must be cleaned from oils, grease or flash rust.

If particular resistance to corrosion or humidity is required, it is suggested the following pretreatment of the surface:

for steel	sand blasting or/and iron or zinc phosphatising
for galvanised steel and aluminium	chromatising

HANDLING AND STORAGE

Store at temperatures lower than 30°C; higher temperatures may damage the powder by causing undesired alterations or agglomerated.

Storage life in original package: 18 months.

TECHNICAL DATA

WAYS OF APPLICATION

Apply by guns with negative terminal (60/80KV) or triboelectric guns automatically or manually.

It is advised to apply in layers with the thickness of 60-80 µ and to stove at 200°C for 10 minutes (temperature of the support).

For stoving of the Polyurethane glossy products it is possible to use the following combinations of time and temperature:

10-15 minutes	200°C (temperature of the support)
15-20 minutes	195°C (temperature of the support)
20-30 minutes	190°C (temperature of the support)

For stoving use the given indications.

TECHNOLOGICAL FEATURES AND RESISTANCE TESTS

The support used	UNI sheet
Thickness	60 microns
Stoving	10 minutes at 200°C
Appearance and levelling	very good

The chemical resistance test was carried out on zinc phosphatised steel.

Code	Int. Method	Range	Ref. Method
------	-------------	-------	-------------

Rev. Date 29/5/2019 Page n. 1 of 2

INVER SpA con Unico Socio

Via di Corticella, 205 - 40128 Bologna (BO) - ITALY

Manufacturing and R&D Labs: Via Marconi 10/A - 40061 Minerbio (BO) ITALY

Ph. +39 051 638 0411 - www.inver.com - inver@sherwin.com

Inver SpA is a member of The Sherwin-Williams Company

SHERWIN-WILLIAMS

Technical Data Sheet

- PU ANTIGRAFFITI GLOSSY

P/CM010	Buchholz indentation test :	more than 90	UNI EN ISO 2815
P/CM181	Pendulum-rocker hardness : Persoz pendulum	more than 300	UNI EN ISO 1522
P/CM040	Erichsen cupping test (mm):	more than 3	UNI EN ISO 1520
P/CM050	Direct impact test (cm.Kg):	more than 10	ASTM D 2794; ISO 6272-2:2002
P/CM170	Conical mandrel : Bend test	maximum 20 mm	UNI EN ISO 6860
P/CM100	Crosscut adhesion (2mm)(GT):	00	UNI EN ISO 2409
P/CM190	Salt fog test :	1000 hours later - indentation along the cross of 3-6 mm	UNI ISO 9227
P/CM230	Resistance to humidity : (Humidity test)	500 hours later - no change	UNI EN ISO 6270-2:2005

NOTE TO USER

The information contained in this document while based on evidence and reliable methods can not be considered exhaustive.

This information are current to the date of issuance of this data sheet, therefore is under user's responsibility to verify that the data provided on this sheet are current to the date of the product.

The user, under its own responsibility, shall respect all the existing provisions on hygiene and safety and shall verify every time the features and the specific and appropriate way to use the product, cause the respect of the provisions is not under producer's direct control.

The manufacturer does not guarantee nor assume any liability or responsibility for whatsoever harm that might result from a misuse of the product or for damages that have arisen after the product's distribution.