

Technical Data Sheet

- PUL MP BT SENZA ALLUMINIO serie 327

GENERAL FEATURES

This thermosetting powder with epoxy and polyester resins is suggested for polymerisation at low temperature (160°C).

The product forms a level hard film with good resistance to mechanical damage.

It has good resistance to yellowing caused by the chain stop during stoving.

APPLICATION

Due to its special content the product has excellent protective and decorative effects. It is particularly suggested for interior coating.

To avoid variation of the metallic effect due to repeated surface rubbing, it is suggested a double coat with transparent powder.

ADVISED CYCLES

The surface to be coated must be cleaned from oils, grease or flash rust.

If particular resistance to corrosion or humidity is required, it is suggested the following pretreatment of the surface:

for steel	sand blasting or/and iron or zinc phosphatising
for galvanised steel and aluminium	chromatising

HANDLING AND STORAGE

Store at temperatures lower than 30°C; higher temperatures may damage the powder by causing undesired alterations or blobs.

Storage life in original package: 18 months.

TECHNICAL DATA

Code	Int. Method	Range	Ref. Method
P/CL092	Calc. specific gravity(kg/l):	1.25 - 1.650	
P/YC060	Particle size dist. <32µm (%):	36 - 46	
P/YC120	Particle size dist. <63µm (%):	74 - 91	
P/CL143	1µm Theor.spread.rate (m2/kg):	540 - 780	

WAYS OF APPLICATION

Apply with automatic or manual guns with negative terminal (60/80KV).

The tribo application depends on the specific plant and must be previously evaluated.

It is advised to apply in layers with the thickness of 60-80 microns and to stove at 160°C for 25 minutes.

For stoving the epoxy polyester BT metallic effect products it is possible to use the following combinations of time and temperature:

10-15 minutes	180°C (temperature of the support)
15-22 minutes	170°C (temperature of the support)
20-30 minutes	160°C (temperature of the support)

For stoving use the indications.

To achieve a consistent color/effect it is important for the coater to establish a ratio of virgin and reclaim powder and adhere to this ratio. Minimum 70% virgin powder should not be reduced.

The virgin powder percentage must be established via upper and lower tolerance samples. A final quality inspection for color is still highly advisable.

TECHNOLOGICAL FEATURES AND RESISTANCE TESTS

The support used	UNI sheet
Thickness	60 microns
Stoving	25 minutes at 160°C
Appearance and levelling	good

Rev. Date 28/5/2019 Page n. 1 of 2

INVER SpA con Unico Socio

Via di Corticella, 205 - 40128 Bologna (BO) - ITALY

Manufacturing and R&D Labs: Via Marconi 10/A - 40061 Minerbio (BO) ITALY

Ph. +39 051 638 0411 - www.inver.com - inver@sherwin.com

Inver SpA is a member of The Sherwin-Williams Company

SHERWIN-WILLIAMS

Technical Data Sheet

- PUL MP BT SENZA ALLUMINIO serie 327

The hardness test was carried out on zinc phosphatised steel.

Code	Int. Method	Range	Ref. Method
P/CM010	Buchholz indentation test :	more than 90	UNI EN ISO 2815
P/CM181	Pendulum-rocker hardness : Persoz pendulum	more than 300	UNI EN ISO 1522
P/CM040	Erichsen cupping test (mm):	more than 3	UNI EN ISO 1520
P/CM050	Direct impact test (cm.Kg):	more than 20	ASTM D 2794; ISO 6272-2:2002
P/CM051	Reverse impact test(cm.kg):	more than 5	ASTM D 2794; ISO 6272-2:2002
P/CM170	Conical mandrel : Bend test	maximum 20 mm	UNI EN ISO 6860
P/CM100	Crosscut adhesion (2mm)(GT):	00	UNI EN ISO 2409
P/CM190	Salt fog test :	1000 hours later - indentation along the cross of 3-6 mm	UNI ISO 9227

NOTE TO USER

The information contained in this document while based on evidence and reliable methods can not be considered exhaustive.

This information are current to the date of issuance of this data sheet, therefore is under user's responsibility to verify that the data provided on this sheet are current to the date of the product.

The user, under its own responsibility, shall respect all the existing provisions on hygiene and safety and shall verify every time the features and the specific and appropriate way to use the product, cause the respect of the provisions is not under producer's direct control.

The manufacturer does not guarantee nor assume any liability or responsibility for whatsoever harm that might result from a misuse of the product or for damages that have arisen after the product's distribution.