



# Protective & Marine Coatings

# SHER-GLASS FF GLASS FLAKE REINFORCED EPOXY

PART A B62-525  
PART B B62V525  
PART B B62V526

SERIES  
STANDARD HARDENER  
LOW TEMP HARDENER

Revised: May 1, 2018

## PRODUCT INFORMATION

4.37

### PRODUCT DESCRIPTION

SHER-GLASS FF is a glass flake reinforced amine epoxy coating formulated for immersion service or where steel or concrete protection is desired, in a wide range of harsh industrial environments.

- The use of pre-wetted glass flake allows for consistent mixing and application
- Re-inforced film enhances performance and edge protection
- Excellent immersion service performance
- Corrosion, impact, abrasion resistant
- Direct to metal application for tanks and structural steel
- Up to 20.0 mils (500 microns) dry in a single coat

### PRODUCT CHARACTERISTICS

<b>Finish:</b>	Semi-Gloss
<b>Color:</b>	Red Oxide, Black, Haze Gray, White OAP
<b>Volume Solids:</b>	76% ± 2% mixed, (calculated)
<b>Weight Solids:</b>	87% ± 2% mixed, (calculated)
<b>Mix Ratio:</b>	4:1 (2 components)
<b>VOC (EPA Method 24):</b>	Unreduced: <250 g/L; 2.08 lb/gal (mixed) 10% Reduced: <276 g/L; 2.30 lb/gal

#### Recommended Spreading Rate per coat:

	Minimum	Maximum
<b>Wet mils (microns)</b>	<b>10.0</b> (250)	<b>26.0</b> (625)
<b>Dry mils (microns)</b>	<b>8.0</b> (200)	<b>20.0</b> (500)
<b>~Coverage sq ft/gal (m<sup>2</sup>/L)</b>	<b>61</b> (1.5)	<b>152</b> (3.7)
<b>Theoretical coverage sq ft/gal (m<sup>2</sup>/L) @ 1 mil / 25 microns dft</b>	<b>1216</b> (29.8)	

*NOTE: Brush or roll application may require multiple coats to achieve maximum film thickness and uniformity of appearance.*

#### Drying Schedule @ 15.0 mils wet (375 microns):

	With B62V525 @ 55°F/13°C	@ 77°F/25°C 50% RH	@ 120°F/49°C
<b>To touch:</b>	7 hours	4 hours	80 minutes
<b>To handle:</b>	9 hours	4.5 hours	90 minutes
<b>To recoat:</b>			
<b>minimum:</b>	48 hours	18 hours	4 hours
<b>maximum:</b>	60 days	60 days	45 days
<b>To cure:</b>	14 days	7 days	3 days
<b>Heat Cure:</b>	8 hours @ ambient, then 16 hours @ 140°F (60°C)		

*If maximum recoat time is exceeded, abrade surface before recoating. Drying time is temperature, humidity, and film thickness dependent.*

<b>Pot Life:</b>	4 hours	2 hours	30 minutes
<b>Sweat-in-time:</b>	30 minutes	15 minutes	none

#### Drying Schedule @ 15.0 mils wet (375 microns):

	With B62V526* @ 40°F/4.5°C	@ 77°F/25°C 50% RH
<b>To touch:</b>	24 hours	2 hours
<b>To handle:</b>	48 hours	2.5 hours
<b>To recoat:</b>		
<b>minimum:</b>	48 hours	8 hours
<b>maximum:</b>	30 days	14 days
<b>To cure:</b>	10 days	5 days
<b>Heat Cure:</b>	8 hours @ ambient, then 16 hours @ 140°F (60°C)	

*If maximum recoat time is exceeded, abrade surface before recoating. Drying time is temperature, humidity, and film thickness dependent.*

<b>Pot Life:</b>	2 hours	30 minutes
<b>Sweat-in-Time:</b>	10 minutes	none

\*Do not use Sher-Glass Low Temp Hardener above 80°F (27°C)

### PRODUCT CHARACTERISTICS (CONT'D)

<b>Shelf Life:</b>	Part A: 24 months Part B: 36 months Store indoors at 40°F (4.5°C) to 100°F (38°C).
<b>Flash Point:</b>	80°F (27°C), PMCC, mixed
<b>Reducer/Clean Up:</b>	Xylene R2K4, or R7K100

### RECOMMENDED USES

For use over prepared steel or concrete in the following environments:

- Petro-chemical and power plants
- Immersion in fresh or salt water
- Water and waste water facilities
- Marine - ships, barges, and offshore structures
- High humidity and moisture areas
- Areas requiring good chemical resistance to splash, spillage, and fumes
- Acceptable for use in areas of high H2S
- Acceptable for use with cathodic protection systems

### PERFORMANCE CHARACTERISTICS

**Substrate\*:** Steel

**Surface Preparation\*:** SSPC-SP10/NACE 2

**System Tested\*:**

1 ct. Sher-Glass FF @ 15.0 mils (375 microns) w/ Standard Hardener  
\*unless otherwise noted below

Test Name	Test Method	Results
<b>Adhesion</b>	ASTM D4541, Patti Tester	1100 psi
<b>Corrosion Weathering Resistance</b>	ASTM D5894, 12 cycles, 4032 hours	Rating 10 per ASTM D714 for Blistering; Rating 10 per ASTM D610 for Rusting
<b>Direct Impact Resistance</b>	ASTM D2794	32 in. lbs.
<b>Dry Heat Resistance</b>	ASTM D2485, Method A, Water Quench Test	400°F (204°C) (discolors)
<b>Flexibility</b>	ASTM D522	6% elongation - Passes 3/4 inch mandrel
<b>Moisture Condensation Resistance</b>	ASTM D4585, 100°F (38°C), 4200 hours	Rating 10 per ASTM D714 for Blistering; Rating 10 per ASTM D610 for Rusting
<b>Pencil Hardness</b>	ASTM D3363	3H
<b>Salt Fog Resistance</b>	ASTM B117, 4200 hours	Rating 10 per ASTM D714 for Blistering; Rating 10 per ASTM D610 for Rusting

Epoxy coatings may darken or yellow following application and curing.



# Protective & Marine Coatings

# SHER-GLASS FF GLASS FLAKE REINFORCED EPOXY

**PART A**      **B62-525**      **SERIES**  
**PART B**      **B62V525**      **STANDARD HARDENER**  
**PART B**      **B62V526**      **LOW TEMP HARDENER**

Revised: May 1, 2018

## PRODUCT INFORMATION

4.37

### RECOMMENDED SYSTEMS

		Dry Film Thickness / ct.	
		Mils	(Microns)
<b>Immersion Service:</b>			
<b>Steel:</b>			
2 cts.	Sher-Glass FF	8.0-20.0	(200-500)
or			
1 ct.	Dura-Plate 235	4.0-8.0	(100-200)
1 ct.	Sher-Glass FF	8.0-20.0	(200-500)
or			
1 ct.	Macropoxy 240	3.0-5.0	(75-125)
1 ct.	Sher-Glass FF	8.0-20.0	(200-500)
<b>Concrete (Smooth):</b>			
1 ct.	Corobond 100	4.0-6.0	(100-150)
2 cts.	Sher-Glass FF	8.0-20.0	(200-500)
<b>Concrete (Rough):</b>			
1 ct.	Steel -Seam FT910, as required to fill voids and provide a continuous substrate, up to 1".*		
2 cts.	Sher-Glass FF	8.0-20.0	(200-500)
<b>Atmospheric Service:</b>			
<b>Steel:</b>			
1-2 cts.	Sher-Glass FF	8.0-20.0	(200-500)
or			
1 ct.	Dura-Plate 235	4.0-8.0	(100-200)
1 ct.	Sher-Glass FF	8.0-20.0	(200-500)
or			
1 ct.	Macropoxy 240	3.0-5.0	(75-125)
1 ct.	Sher-Glass FF	8.0-20.0	(200-500)
<b>Steel, Urethane topcoat:</b>			
1 ct.	Sher-Glass FF	8.0-20.0	(200-500)
1 ct.	Acrolon 218 HS Polyurethane	3.0-6.0	(75-150)

\*Kem Cati-Coat Epoxy Filler/Sealer may also be acceptable.

The systems listed above are representative of the product's use, other systems may be appropriate.

### DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.

### SURFACE PREPARATION

Surface must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion.

Refer to product Application Bulletin for detailed surface preparation information.

Minimum recommended surface preparation:

**Iron & Steel:**  
**Atmospheric:** SSPC-SP12/NACE 5, WJ-4 (with existing profile) or SSPC-SP3 or SSPC-SP2  
 SSPC-SP10/NACE 2, 2-3 mil  
**Immersion:** (50-75 micron) profile or SSPC-SP12/NACE 5, WJ-2/SC-2 (with existing profile)

**Concrete & Masonry:**  
**Atmospheric:** SSPC-SP 13/NACE 6, or ICRI No. 310.2R, CSP 1-3  
**Immersion:** SSPC-SP 13/NACE 6, 6-4.3.1 or 4.3.2, or ICRI No. 310.2R, CSP 1-3

#### Surface Preparation Standards

Condition of Surface	ISO 8501-1 BS7079:A1	Swedish Std. SIS055900	SSPC	NACE
White Metal	Sa 3	Sa 3	SP 5	1
Near White Metal	Sa 2.5	Sa 2.5	SP 10	2
Commercial Blast	Sa 2	Sa 2	SP 6	3
Brush-Off Blast	Sa 1	Sa 1	SP 7	4
Hand Tool Cleaning	Rusted C St 2	C St 2	SP 2	-
Pitted & Rusted	D St 2	D St 2	SP 2	-
Rusted	C St 3	C St 3	SP 3	-
Power Tool Cleaning	Pitted & Rusted D St 3	D St 3	SP 3	-

### TINTING

Do not tint.

### APPLICATION CONDITIONS

**Temperature:**  
 Standard Hardener: Air & Material 55°F (13°C) minimum  
 Surface 120°F (49°C) maximum  
 Low Temp Hardener: Air & Material 40°F (4.5°C) minimum  
 Surface 120°F (49°C) maximum  
 At least 5°F (2.8°C) above dew point.  
 Relative humidity: 85% maximum

Refer to product Application Bulletin for detailed application information.

Do not use low temperature hardener above 80°F (27°C)

### ORDERING INFORMATION

**Packaging:** 5 gallons (18.9L) mixed  
**Part A:** 4 gallons (15.1L) in a slack filled five gallon container  
**Part B:** 1 gallon (3.78L)  
**Weight:** 11.54 ± 0.3 lb/gal ; 1.4 Kg/L (mixed)

### SAFETY PRECAUTIONS

Refer to the MSDS sheet before use.

Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.

### WARRANTY

The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.





# Protective & Marine Coatings

# SHER-GLASS FF GLASS FLAKE REINFORCED EPOXY

PART A B62-525  
PART B B62V525  
PART B B62V526

SERIES  
STANDARD HARDENER  
LOW TEMP HARDENER

Revised: May 1, 2018

## APPLICATION BULLETIN

4.37

### APPLICATION PROCEDURES

Surface preparation must be completed as indicated.

Mix contents of each component thoroughly with low speed power agitation. Make certain no pigment remains on the bottom of the can. Then combine 4 parts by volume of Part A with one part by volume of Part B. Thoroughly agitate the mixture with power agitation at slow speeds. Allow the material to sweat-in as indicated. Prior to use, pour through a 30-60-mesh screen and re-stir before using.

If reducer solvent is used, add only after components have been thoroughly mixed, after sweat-in.

Apply paint at the recommended film thickness and spreading rate as indicated below:

#### Recommended Spreading Rate per coat:

	Minimum	Maximum
Wet mils (microns)	10.0 (250)	26.0 (625)
Dry mils (microns)	8.0 (200)	20.0 (500)
~Coverage sq ft/gal (m <sup>2</sup> /L)	61 (1.5)	152 (3.7)
Theoretical coverage sq ft/gal (m <sup>2</sup> /L) @ 1 mil / 25 microns dft	1216 (29.8)	

NOTE: Brush or roll application may require multiple coats to achieve maximum film thickness and uniformity of appearance.

#### Drying Schedule @ 15.0 mils wet (375 microns):

	@ 55°F/13°C	@ 77°F/25°C 50% RH	@ 120°F/49°C
To touch:	7 hours	4 hours	80 minutes
To handle:	9 hours	4.5 hours	90 minutes
To recoat:			
minimum:	48 hours	18 hours	4 hours
maximum:	60 days	60 days	45 days
To cure:	14 days	7 days	3 days
Heat Cure:	8 hours @ ambient, then 16 hours @ 140°F (60°C)		
If maximum recoat time is exceeded, abrade surface before recoating. Drying time is temperature, humidity, and film thickness dependent.			
Pot Life:	4 hours	2 hours	30 minutes
Sweat-in-time:	30 minutes	15 minutes	none

#### Drying Schedule @ 15.0 mils wet (375 microns):

	@ 40°F/4.5°C	@ 77°F/25°C 50% RH
To touch:	24 hours	2 hours
To handle:	48 hours	2.5 hours
To recoat:		
minimum:	48 hours	8 hours
maximum:	30 days	14 days
To cure:	10 days	5 days
Heat Cure:	8 hours @ ambient, then 16 hours @ 140°F (60°C)	
If maximum recoat time is exceeded, abrade surface before recoating. Drying time is temperature, humidity, and film thickness dependent.		
Pot Life:	2 hours	30 minutes
Sweat-in-Time:	10 minutes	none
*Do not use Sher-Glass Low Temp Hardener above 80°F (27°C)		

Application of coating above maximum or below minimum recommended spreading rate may adversely affect coating performance.

### PERFORMANCE TIPS

Stripe coat all crevices, welds, and sharp angles to prevent early failure in these areas.

When using spray application, use a 50% overlap with each pass of the gun to avoid holidays, bare areas, and pinholes. If necessary, cross spray at a right angle.

Spreading rates are calculated on volume solids and do not include an application loss factor due to surface profile, roughness or porosity of the surface, skill and technique of the applicator, method of application, various surface irregularities, material lost during mixing, spillage, overthinning, climatic conditions, and excessive film build.

Excessive reduction of material can affect film build, appearance and adhesion.

Excessive film build, poor ventilation, and cool temperatures may cause solvent entrapment and premature coating failure.

**For Immersion Service:** (if required) Holiday test in accordance with ASTM D5162 for steel, or ASTM D4787 for concrete.

Do not mix previously catalyzed material with new.

Do not apply the material beyond recommended pot life.

Do not use the Low Temp Hardener above 80°F (27°C)

Refer to Product Information sheet for additional performance characteristics and properties.

### CLEAN UP INSTRUCTIONS

Clean spills and spatters immediately with R2K4, or R7K100. Clean tools immediately after use with R2K4, or R7K100. Follow manufacturer's safety recommendations when using any solvent.

### DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.

### SAFETY PRECAUTIONS

Refer to the MSDS sheet before use.

Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.

### WARRANTY

The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.