



WET-DRY ROOF CEMENT 58-600 BLACK

PRODUCT DESCRIPTION

Uniflex® Wet-Dry Roof Cement is a single component, asbestos free, asphalt-based cement designed for roof application. Uniflex Wet-Dry Roof Cement is especially suited for asphaltic based roofing substrates. Seals quickly, will not pull apart or lose its bond, remains soft and pliable, and resists temperature change. Can be applied to wet or dry surfaces, even underwater.

GENERAL USES

Roof maintenance, patching, sealing and repairing roof flashing.

PACKAGING INFORMATION

SKU	SIZE
KST058600-01	10 oz cartridge, black
KST058600-16	1-gallon, black
KST058600-30	3-gallon, black
KST058600-20	5-gallon, black

APPLICATION CONDITIONS

KEEP FROM FREEZING. Refer to product application bulletin for detailed application information.

Primer not required on most applications. For best results, remove dust, dirt, and loose materials with a stiff brush or broom. Remove old sealant or roof coatings. Surfaces must be clean.

APPLICATION PROCEDURES

APPLICATION/TOOLING: Apply with standard caulking gun, trowel, or putty knife, tooling into seams and cracks. Extend Uniflex Wet-Dry coverage 3" to 4" beyond problem area to ensure seal. Apply at a rate of 1/8" per coat, not exceeding 1/4" in thickness.

WARRANTY

This product is manufactured in accordance to ISO 9001-2008 standards. Seller and manufacturer's only obligation shall be to replace such quantity of product proved to be defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential arising from the use or the inability to use the product for his/her intended use, and user assumes all risk and liability. Color fade is not covered under warranty.

PRODUCT CHARACTERISTICS

Color	Black
Vehicle Base	Asphalt-Based
Dry Time	
Tack Free (ASTM 879)	60 min
Cure Time	3 days
	<i>Drying Time is temperature, humidity and film thickness dependent</i>
VOC	<260 g/L
Shelf life	1 year (unopened)

PERFORMANCE CHARACTERISTICS

Dry Adhesion (lbf)	
Aluminum	2.3/100c
Brick	4.3/100c
Luan (Wood)	3.3/100c
Modified Bitumen	0.6/100a
Shingle	2.6/100c
Steel	3.4/100c
Type "A" Hardness	32

THEORETICAL YIELD (PER 10 FL OZ CARTRIDGE)

Joint Size	Linear Feet
1/4"-1/4"	24.1
1/4"-3/8"	16.0
1/4"-1/2"	12.0
1/2"-3/8"	8.4
1/2"-1/2"	6.0

PER GALLON

1/8"-1/4"	10-15 sq ft/gallon
-----------	--------------------

DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of KST Coatings- A Business Unit of the Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of the publication. Consult your Uniflex Technical Representative to obtain the most recent Product Data Information.

If further information is needed, contact Uniflex Technical Service at
1-888-321-3539

