



White Lightning®
Siliconized Latex Glazing Compound
WL08012

Physical Properties:

Type:	Siliconized Latex Glazing Compound
Color:	White
Shelf Life:	12 months
Flash point:	N/A - Waterbased
Flammability:	N/A - Waterbased
Cure Time:	2-5 Days
Tack Free Time:	30 – 60 minutes
Application Temperature:	Above 50 F
VOC Level:	0.464 lbs / gal
Mildew Resistance:	Excellent
Odor:	Low
Shrinkage:	Low / None
Vehicle:	Water
Weight per gallon:	15.32 lbs/gal

Performance:

Joint movement capability:	Good
Bead sizes (suggested):	1/8" x 1/8" – 3/8" – 3/8"
Freeze / thaw stability:	Passes 5 cycles
Clean-up:	Water
Flexibility:	Excellent
Painting:	Paintable within 4-6 hours
Water resistance:	Good

Surface Preparation: Apply to clean, dry surface. For best results, surface should be primed before glazing.

Precautions: Do not use in areas subject to water. Keep from freezing.

Size	Order#	UPC
10 oz cartridge	WL08012	0-23275-08012-6

White Lightning Products
101 Prospect Ave NW
Cleveland, OH 44115
1-800-241-5295
6/2017